

# ARDROX<sup>®</sup> 906

## Water Washable Visible Penetrant

### Type II (Visible Dye), Method A (Water Washable) and Method C (Solvent Removable), AMS 2644 Approved Inspection Penetrant

---

#### PRIMARY APPLICATION

ARDROX<sup>®</sup> 906 is a water washable color contrast penetrant, widely used in many industries for the detection of indications which are open to the surface of non-porous parts. ARDROX 906 is a dark red in color, allowing easy control and monitoring of the washing process.

ARDROX 906 is a high-sensitivity, low- viscosity liquid with excellent surface wetting properties to ensure optimum coverage of the part. It is used in conjunction with developers and a penetrant remover which can be water or a suitable organic solvent as a part of the inspection technique.

Defects such as cracks, laps, cold shuts, porosity, bursts, casting and welding discontinuities can be detected using the appropriate process. ARDROX 906 has been formulated to ensure the product has improved resistance to over-washing where removal by water spray is the preferred method. ARDROX 906 is designed to be used with a non-aqueous developer such as ARDROX 9D1B or ARDROX NQ1.

#### CHEMICAL CHARACTERISTICS

Physical Form .....	Deep red
Bulk Density .....	0.926 g/ml at 68°F (20°C)
Flash Point .....	200°F (93°C) minimum, ASTM D113 (PMCC)
Sulfur Content .....	<1000 ppm
Chloride Content .....	<1000 ppm
Density .....	0.926 g/ml at 68°F (20°C)

#### APPROVALS

ARDROX 906 is approved by AMS 2644, NAVSEA 250-1500-1, & ASME Pressure Vessel & Boiler Code. Check with your Chemetall representative for complete approvals.

#### APPLICATION PROCEDURE

ARDROX 906 may be applied by aerosol, brush, tank immersion, conventional or electrostatic spray. The following typical process sequence illustrates the recommended method of use.

#### PRECLEAN/DRY

Completely remove all surface contamination (rust, paint residues, greases, scale, etc.). After cleaning, make sure that the component is completely dry and cool, 120°F (49°C) or lower, before applying the penetrant. ARDROX 9PR50 solvent-based products may be used as oil and grease cleaners/removers.

## **PENETRANT APPLICATION**

Apply penetrant to the surface and leave on for a suitable dwell period. If the contact period exceeds 120 minutes, the penetrant should be reapplied to the surface.

### **AMS 2644, METHOD A, PENETRANT REMOVAL: WATER WASH**

Water washes in accordance with the relevant specification or Code.

Use either one or a combination of manual spray or automatic spray tank rinses.

To accelerate drying time, use wash water at upper limit temperatures.

### **AMS 2644, METHOD C, PENETRANT REMOVAL: WIPE OFF**

Wipe excess penetrant from surface with a clean cloth. Moisten a clean cloth with ARDROX 9PR50 or ARDROX PR1 and wipe surface free of penetrant residue. To maintain sensitivity, do not flood surface with cleaner/remover.

## **OVEN DRY, AIR RECIRCULATING**

Maximum oven temperature: 160°F (71°C)

Use the minimum time necessary to thoroughly dry the components. Use clean, filtered, low-pressure compressed air to remove pockets of water before oven drying. If a drying oven is not available, accelerate drying time by blowing warm air across the part.

## **APPLY DEVELOPER**

Apply non-aqueous developers ARDROX 9D1B or NQ1 by spray; dwell time is the dry time plus two minutes.

## **INSPECTION**

Components should be inspected under bright light (e.g. 100 ft. candle). A pinkish developer film indicates incomplete surface penetrant removal. Severe penetrant residue will mask fine indications.

## **NOTES ON USE** (see Material Safety Data Sheet)

ARDROX 906 is non-corrosive, safe to use on all metal alloys and meets AMS 2644 corrosion requirements.

ARDROX 906 will stain or soften some plastics, rubbers or ceramics; where appropriate, perform a compatibility test.

## **SAFETY AND HANDLING**

Prior to handling and use of any of the materials referenced in this document, the Material Safety Data Sheets should be read and understood by all personnel in contact with these materials.

## **KEEP OUT OF REACH OF CHILDREN**

## STORAGE

Dry indoor storage at temperatures between 40°F and 100°F (4.4°C and 37.8°C) is recommended, away from any incompatible materials referenced in the Material Safety Data Sheets. All containers should be tightly closed when not in use.

## SHELF LIFE

The shelf life for ARDROX 906 is 3 years.

## DISPOSAL

Any disposal of the materials referenced in this document should be in accordance with all applicable federal, state, providential and local regulations. The process solution can contain components other than those present in the materials as supplied. Analysis of process solutions may be required prior to disposal.

Chemetall US, Inc. ("Chemetall") warrants that this product or products described herein will conform with its published specifications. The products supplied by Chemetall and information related to them are intended for use by buyers having necessary industrial skill and knowledge. Buyers should undertake sufficient verification and testing to determine the suitability of the Chemetall materials for their own purpose. Since buyer's conditions of use of products are beyond Chemetall's control, Chemetall does not warrant any recommendations and information for the use of such products. CHEMETALL DISCLAIMS ALL OTHER WARRANTIES INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH THE USE OF ITS PRODUCTS.

**Chemetall**



ISO 9001/FM 93653